

09/530,202

ABSTRACT

alt
1cc
In order to provide
~~There is provided~~ a vinyl chloride resin composition, which is
excellent in processability and can produce a processed article having
5 excellent physical property or a formed molding having excellent
property, ^a processing aid having specific viscosity of at least 0.5 is
combined with a vinyl chloride resin, wherein the aid is obtained by
polymerizing 1 to 50 parts by weight of a monomer mixture (B)
comprising 0 to 49 % by weight of methyl methacrylate, 51 to 100 % by
10 weight of at least one monomer selected from the group consisting of a
methacrylate ester except methyl methacrylate and an acrylate ester,
and 0 to 20 % by weight of a vinyl monomer copolymerizable therewith,
in the presence of a latex of a (co)polymer having specific viscosity of at
least η_{sp} 0.7, which is obtained by polymerizing in emulsion 99 to 50
15 parts by weight of a monomer mixture (A) comprising 51 to 100 % by
weight of methyl methacrylate, 0 to 49 % by weight of at least one
monomer selected from the group consisting of a methacrylate ester
except methyl methacrylate and an acrylate ester, and 0 to 20 % by
weight of a vinyl monomer copolymerizable therewith, wherein the total
20 amount of (A) and (B) is 100 parts by weight.